1-8.   (Cancelled)

9.   (Currently Amended)   A fiber yarn which is a yarn containing a bamboo pulp ~~cellulose~~ filament having about 80 wt% to about 87.5 wt% of an α-cellulose component and having a thickness of about 10 to about 600 dtex and number of twist of 0 to about 3,000 T/M.

10.   (Currently Amended) The fiber yarn according to claim 9, wherein the filament is 85 wt% ~~or more~~ <u>to 87.5% wt%</u> of α-cellulose component.

11.   (Previously Presented) The fiber yarn according to claim 9, wherein a total amount of α- and β-cellulose component in said filament is about 90 wt% or more.

12.   (Previously Presented) The fiber yarn according to claim 9, wherein the filament is produced by a continuous spinning system of viscose rayon process.

13.   (Previously Presented) The fiber yarn according to claim 9, wherein the fiber yarn contains at least about 20 wt% of said filament and another fiber that is at least one fiber selected from the group consisting of natural fiber, regenerated fiber, semi-synthetic fiber and synthetic fiber.

14.   (Cancelled)

15.   (Previously Presented) The fiber yarn according to claim 13, wherein the filament and the another fiber are made into a composite by any one method selected from the group consisting of doubling and twisting, covering, filament mixing, false twisting and spinning intersection twist.

16.   (Previously Presented) A cloth comprising a woven or knitted fabric or a non-woven fabric comprising the fiber yarn according to claim 9.

17.   (Previously Presented) The fiber yarn according to claim 9, wherein the filament

is 87 wt% or more of α-cellulose component.

18   (Currently Amended) A fiber yarn which is a yarn containing a bamboo pulp ~~cellulosic~~ filament having about 80 wt% to about 87.5 wt% of an α-cellulose component.

19.   (Previously Presented) The fiber yarn according to claim 18, further containing a β-cellulose component such that the amount of α- and β-cellulose components in the filament is 90 wt% or more.

20-26. (Cancelled)

.